



Emulsion Selection Guide for Adhesives & Sealants

Product Features	Suggested Applications									
	Sealants	Pressure Sensitive	Lamination	Polychloroprene Blending Agent	FDA Approved	Polymer NVM (%)	Tg (°C)	Tensile Strength (psi)	Elongation @ Break (%)	Heat Resistance (°C)
EPS 2111 Good 180° peel resistance with PVC, no loss of adhesion over extended aging.	●		●	●		55	-5	351	360	75
EPS 2113 Broad adhesion, good peel, tack & static shear.	●	●	●			57	-45	na	na	<40
EPS 2141 Ideal for sealants, excellent early water resistance, alkali resistance and flexibility. Good adhesion over various substrates.	●		●	●		50	-15	72	>600	62
EPS 2143 Broad adhesion, good peel, heat resistance, & no tack. No loss of adhesion over extended aging.		●		●		45	-10	101	>650	55

02/04/10

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.