



EPS-MATERIALS 1400 NORTH STATE STREET MARENGO, IL 60152

p: 800.618.4111 f: 815.568.4155 www.eps-materials.com

PRODUCTS DESIGNED FOR THE ARCHITECTURAL MARKET

Interior Applications

Product	Polymer NVM	pH	MFFT (°C)	Coalescing Solvent (on binder nvm)	Description
WALL & TRIM - FLAT TO SEMI GLOSS					
EPS 2792	50.0	8.5 – 9.0	< 5	4% Texanol	All-acrylic emulsion that is an excellent choice for high performance flat through semi-gloss interior architectural and institutional coatings. Environmentally friendly polymer with a low coalescent demand and does not contain APEO raw materials. Superior scrub resistance.
STAIN-BLOCKING PRIMERS					
EPS 2533	45.5	7.0 - 8.0	9	5 - 6% Texanol	Excellent adhesion, ink and tannin stain-blocking, early water resistance and corrosion resistance. Ideal for use as a universal primer or low gloss topcoat on ferrous and non-ferrous metal, cementitious, wood and plastic substrates. A great low VOC waterborne alternative to solvent-based primers.
INTERIOR WOOD FINISHES					
EPS 2545	30.0	9.0 - 10.0	1	No coalescing solvent needed	Acrylic dispersion with excellent penetration and re-solubility properties for interior stain applications. Also useful for alkali strippable temporary coatings.
EPS 2538	40.0	9.0 - 10.0	56	15% DPnB	Room temperature self-crosslinking emulsion for all clear applications on wood, plastic and cementitious substrates where hardness development is demanded.
EPS 2539	40.0	6.5 - 7.5	57	15 - 20% DPnB	Room temperature self-crosslinking emulsion for all clear applications on wood, plastic and cementitious substrates where minimal color change is required.
EPS 4213	33.0	7.7 - 8.3	na	none required	Oxidizing polyurethane dispersion offering fast dry, hardness development and chemical resistance for wood flooring.

rev 09/09

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option