



## Cementitious Substrates

### Stains & Sealers

Product	NVM	MFFT °C	Properties	Applications
EPS 2293	40.0	<10	<ul style="list-style-type: none"> <li>• Excellent early water resistance</li> <li>• Excellent blush resistance</li> <li>• Excellent wet and dry adhesion</li> <li>• &lt;100 g/l clear formulations with freeze-thaw stability</li> <li>• Excellent UV and chemical resistance</li> </ul>	<ul style="list-style-type: none"> <li>• Clear high gloss sealers</li> <li>• Satin finish sealers</li> <li>• Semi-Transparent stains</li> <li>• Solid color stains</li> <li>• Floor paints</li> </ul>
EPS 2257	40.0	<5	<ul style="list-style-type: none"> <li>• Good water resistance</li> <li>• Good blush resistance</li> <li>• Excellent UV resistance / non-yellowing</li> <li>• Able to formulate &lt; 100 g/l VOC</li> </ul>	<ul style="list-style-type: none"> <li>• Clear sealers</li> <li>• Semi-Transparent stains</li> </ul>

rev. 09/24/09

**Questions? Call EPS Technical Service @ 1-800-601-8111**

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.