



Urethane Resins for Wood Flooring & Clear Finishes

HIGH SOLIDS OIL MODIFIED URETHANES

PRODUCT	NVM	WPG	OIL TYPE	SOLVENT	ACID #	VISC.	VISC. Reduced	COLOR	Sward Hardness	NOTES
EPS 4860	70.0%	7.80	Mixed	LAMS/HFMS /A100 /Dipentene	3 Max.	M-U		6 Max.	30	<ul style="list-style-type: none"> • Best single resin 350 g/L • Lowest viscosity • High gloss thru flat • <i>Ethyl Benzene non-reportable</i>
EPS 4854	70.0%	7.87	Mixed	LAMS/A100	2 Max.	S-U	N/A	6 Max.	25	<ul style="list-style-type: none"> • Improved thru dry and hardness development • Low viscosity • High gloss thru flat • <i>Ethyl Benzene non-reportable</i>
EPS 4843	80.0%	7.93	Soya	LAMS/A100	3 Max.	Z-Z3	F-H @ 65%	5 Max.	14	<ul style="list-style-type: none"> • Good hardness • Good abrasion resistance • Moderate dry • <i>Ethyl Benzene non-reportable</i>

LAMS = Low Aromatic (<1%), Rule 66, Mineral Spirits; HFMS = High Flash Mineral Spirits

Questions? Call EPS Technical Service @ 1-800-601-8111

rev 10/09

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.