



# Urethane Resins for Wood Flooring & Clear Finishes

## CONVENTIONAL SOLIDS OIL MODIFIED URETHANES AND URALKYDS

PRODUCT	NVM	WPG	OIL TYPE	SOLVENT	ACID #	VISC.	VISC. Reduced	COLOR	Sward Hardness	NOTES
<b>EPS 4429</b>	60.0%	7.67	Soya	LAMS	2 Max.	Z <sub>1</sub> -Z <sub>3</sub>	C-E @ 50%	6 Max.	50	<ul style="list-style-type: none"> <li>Fast dry, abrasion resistance, less yellowing</li> <li>High gloss thru flat</li> </ul>
<b>EPS 4402</b>	60.0%	7.60	Linseed	LAMS	2 Max.	Y-Z <sub>2</sub>		6 Max.	60	<ul style="list-style-type: none"> <li>Very fast dry and early hardness development</li> <li>Sealers and sports flooring</li> </ul>
<b>EPS 4627**</b>	60.0%	7.66	Mixed	LAMS /A100	3 Max.	U-V	N/A	6 Max.	44	<ul style="list-style-type: none"> <li>Fast dry with fast hardness development</li> <li>Low viscosity</li> <li>High gloss thru flats</li> <li>Blending vehicle for 350 VOC varnish</li> </ul>
<b>EPS 4655</b>	55.0%	7.60	Soya	LAMS /A100	4 Max.	X-Z <sub>1</sub>	C-F @ 48%	4 Max.	48	<ul style="list-style-type: none"> <li>Fast dry, abrasion resistance and less yellowing</li> <li>Fast Viscosity reduction</li> <li><i>Ethyl Benzene Non-Reportable</i></li> </ul>
<b>EPS 4681</b>	50.0%	7.48	Soya	LAMS /A100	2 Max.	Y-Z <sub>1</sub>	N-P @ 45%	4 Max.	60	<ul style="list-style-type: none"> <li>Fast dry, and less yellowing</li> <li>High hardness</li> <li>Sealers and sports flooring</li> <li><i>Ethyl Benzene Non-Reportable</i></li> </ul>
<b>EPS 4401</b>	50.0%	7.45	Linseed	LAMS	3 Max.	Z <sub>+</sub> -Z <sub>4</sub>	N/A	6 Max.	60	<ul style="list-style-type: none"> <li>Fast dry, hardness and abrasion resistance</li> <li>Excellent for sealers and sports flooring</li> <li>High gloss thru flat</li> </ul>

LAMS = Low Aromatic (<1%), Rule 66, Mineral Spirits; A100 – High Flash (100) Aromatic Naphtha

\*\*For lower cost, the 60% Uralkyd we offer is EPS 4603 (Soya-based) in LAMS & Xylene

**Questions? Call EPS Technical Service @ 1-800-601-8111**

rev 10/09

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.