



## Resins for Wood Flooring & Clear Finishes

### EMULSION FOR SANDING SEALER AND FLOOR VARNISH

PRODUCT	NVM	WPG	pH	MFFT	PROPERTIES	APPLICATIONS
EPS 2538	40.0%	8.70	10.0-10.5	56°C	<ul style="list-style-type: none"><li>▪ Self crosslinking styrenated emulsion</li><li>▪ Chemical Resistance</li><li>▪ Wear resistant</li><li>▪ Mar resistant</li></ul>	<ul style="list-style-type: none"><li>• Sanding sealer</li><li>• Blend vehicle with PUD for floor finishes</li></ul>

### EMULSIONS FOR STAINS

PRODUCT	NVM	WPG	pH	MFFT	PROPERTIES	APPLICATIONS
EPS 2257	40.0%	8.80	8.0-9.0	7°C	<ul style="list-style-type: none"><li>▪ All-acrylic emulsion</li><li>▪ Small particle size, excellent penetration</li><li>▪ Non-yellowing</li></ul>	<ul style="list-style-type: none"><li>• Exterior wood and concrete stains</li></ul>
EPS 2293	40.0%	8.70	8.0-9.0	<10°C	<ul style="list-style-type: none"><li>▪ Self crosslinking, all-acrylic emulsion</li><li>▪ Chemical resistance</li><li>▪ Abrasion resistance</li></ul>	<ul style="list-style-type: none"><li>• Exterior clear sealers for wood and concrete</li></ul>
EPS 2545	30.0%	8.60	9.0-10.0	1°C	<ul style="list-style-type: none"><li>▪ Styrenated acrylic dispersion</li><li>▪ Small particle size, excellent penetration</li></ul>	<ul style="list-style-type: none"><li>• Interior wiping stains</li></ul>

Questions? Call EPS Technical Service @ 1-800-601-8111

rev 10//09

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.